



# GALVEX 17.89 SUPRA

Liquid detergent, slightly alkaline, used in finishing bath for removing polishing compounds during ultrasonic processes.

## COMPATIBILITY:

- Sensitive steel (types of steel used in watches: 20AP, H1...)
- Copper alloys (brass)
- Gold
- Copper-beryllium
- Decorative coatings
- Silver

## INGREDIENTS:

- Surfactants, solubilising agents, chelating agents
- Phosphate-free product

## PHYSICAL AND CHEMICAL DATA:

- pH concentrated: 9.5
- pH (1%): 9.3
- Density: 1.042
- TSurface tension: 28.1 mN/m

## INSTRUCTIONS FOR USE:

Optimum use conditions may be affected by the quality of the water used in the baths, as well as the type and quantity of contaminants.

- Concentration: 3 to 5%
- Temperature: 50 to 75°C (122 à 167°F)
- Time: 30 sec to 5 min.

When cleaning between operations low temperature can be used: 50 - 60°C (122 à 140°F).

## PROCESS EXAMPLES:

Cleaning of sensitive steel parts (20 AP)

Pollution: removal of oils and polishing compounds



## BENEFITS:

- Product for pre-soaking, cleaning and finishing for removal of polishing compounds
- Excellent emulsification and solubilisation of greases
- Dispersion of contaminations
- Perfect degreasing, spotless finish
- Antioxydation properties, protects sensitive alloys without attacking the surface
- Spotless drying after rinsing (Hydrophobic surface)
- Shiny and spotless surfaces after drying

05/07/21

## STORAGE CONDITIONS:

- Keep the recipient hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging.



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

