



# RODACLEAN SUPRA

Highly alkaline liquid product for removing residues of polishing compounds and oils residues in ultrasonic processes.

## COMPATIBILITY:

- Titanium
- Ceramics
- Steels/stainless steels

**Incompatibility:** aluminium, zamak, nickel silver and copper alloys

## INGREDIENTS:

- Strong alkalis, surfactants, phosphates
- Chelating agents

## PHYSICAL AND CHEMICAL DATA:

- pH concentrated: 14
- pH (1%): 12.5
- Density: 1.238
- Surface tension: 29.2 mN/m


## INSTRUCTIONS FOR USE:

The optimum conditions for use are affected by the quality of the water used in the baths and the type and quantity of contaminants.


- Concentration: 3 to 10%
- Temperature: 40 to 70°C (104 à 158°F)
- Time: 3 to 5 minutes

## PROCESS EXAMPLES:

- Cleaning of stainless steel or titanium prosthetics / Pollution: oils, polishing compounds



- Cleaning of watch-making supplies / Pollution: polishing compounds



## BENEFITS:

- Excellent preparation of surfaces after polishing and machining and before vacuum metallisation
- Adapted for titanium (dental, medical and orthopaedic implants, dental and surgical implants)
- Removal of dry contaminants
- Perfect emulsification and solubilisation of greasy residues
- Protection against corrosion (Water-repellent surface)
- Long bath life

24/11/17



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

