



GALVAPREP 707

Highly acidic powder product elaborated for the neutralization and activation of cuprous metals in ultrasonic processes.

COMPATIBILITY

- Copper/Beryllium, cuprous metals

INGREDIENTS

- Acidic, surfactants
- Phosphates
- Fluorides

PHYSICAL AND CHEMICAL DATA

- pH (3%): 3.0
- Density: n.m
- Surface tension: 30.7 mN/m

INSTRUCTIONS FOR USE


Optimum use conditions may be affected by the quality of the water used in the baths, as well as the type and quantity of contaminants.

- Concentration: 40 to 60 g/L
- Temperature: 20 to 30°C (68 to 86°F)
- Time: 10 to 30 sec.

Tip: bath must be prepared with hot water (40°C / 104°F), before to add the product

PROCESS EXAMPLE

- Preparation prior to electroplating



*Note: not compatible with Zamak



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

NGL CLEANING TECHNOLOGY SA - ECOLOGICAL CLEANING SOLUTIONS

Chemin de la Vuarpillière 7 // CH-1260 NYON // SWITZERLAND
+41 22 365 46 66 // contact@ngl-group.com // www.ngl-group.com



BENEFITS

- Complete removal of light oils, polishing compounds, powders, finger prints
- Effective on cuprous metals
- Perfect electroplating
- Deoxidation of copper alloys
- Brighten surfaces
- Suitable for finishing, easy rinse off
- Exceptional longevity of the baths

20/05/21