



GALVEX 20.31

Mild alkali product, for the removal of glues or lacquers in ultrasonic processes, or surface preparation prior to electroplating.

COMPATIBILITY

- Steel/Stainless steel
- 20 AP
- CuBe
- Unleaded brass or with lead

INGREDIENTS

- Surfactants
- Solvent
- Chelating agents

PHYSICAL AND CHEMICAL DATA

- pH concentrated: 10.08
- pH (1%): 10.16
- Density: 1.029
- Surface tension: 31,4 mN/m

INSTRUCTIONS FOR USE

Optimum use conditions may be affected by the quality of the water used in the baths, as well as the type and quantity of contaminants

- Concentration: 2 to 5%
- Temperature: 50 to 70°C (122 to 158°F)
- Time: 2 to 5 minutes

PROCESS EXAMPLES

- Glues and lacquers removal

CLEANING



US

- Surface preparation prior to electroplating

CLEANING



US

US

BENEFITS

- No harmful compounds
- Perfect removal of lacquers and glues
- None flammable, increased safety and storage conditions
- Excellent degreasing before electroplating
- Effective deoxidation of cuprous materials
- Excellent surface wettability

12/11/21

CONDITIONS DE STOCKAGE

- Keep the recipient hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging.



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

NGL CLEANING TECHNOLOGY SA - ECOLOGICAL CLEANING SOLUTIONS

Chemin de la Vuarpillière 7 // CH-1260 NYON // SWITZERLAND
+41 22 365 46 66 // contact@ngl-group.com // www.ngl-group.com

