



HELIT

Neutral universal detergent, with hydrophilic effect for superfinish of surfaces in ultrasonic process prior drying.



JEWELLERY RANGE

FUNCTION	APPLICATION/POLLUTION
Hydrophilic superfinish	Light pollutions

COMPATIBILITY

- Stainless steel
 - Lead-free brass
 - Silver: 800 - 925 (sterling)
 - Gold: white, pink, yellow
 - Platinum
 - Acetate
 - Rhodium, palladium
 - Stones*:
 - Diamond, sapphire, ruby, emerald
 - Zirconium, ceramic
- *Please contact NGL before implementing a process.

COMPONENTS

- Surfactants
- No phosphates, no NTA

PHYSICOCHEMICAL DATA

- pH concentrated: 6.9
- Density: 1.04
- Surface tension: 27.9 mN/m

INSTRUCTIONS FOR USE*

- Concentration: 3 to 5%
- Temperature: 40 to 70°C
- Time: 2 to 4 minutes

*Dependent on the quality of the water and the nature and quantity of contaminants.

PROCESS EXAMPLE

- Finishing cleaning


CLEANING

GALVEX 20.02 Tap water Conc.: 2-5% Temp.: 40-70°C 104-158°F Time: 3-5 min	TAP WATER RINSE Temp.: 20-30°C 69-86°F Time: 3-5 min	HELIT Tap water Conc.: 3-5% Temp.: 40-70°C 104-158°F Time: 2-4 min	TAP WATER RINSE Temp.: 20-30°C 69-86°F Time: 3-5 min	DI WATER RINSE Temp.: 20-30°C 69-86°F Time: 3-5 min	DI WATER RINSE Temp.: 20-30°C 69-86°F Time: 3-5 min	HOT AIR DRYING
---	--	--	--	---	---	-----------------------

US

US

HYDROPHILIC FINISH



07/06/22

STORAGE CONDITIONS

- Keep the recipient hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging (PEHD).



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

