



RODASTEL 30

Liquid acid product, used for deoxidation, neutralization and activation of surfaces prior to vacuum or electrolytic plating, in ultrasonic processes.



JEWELLERY RANGE

FUNCTION	APPLICATION/POLLUTION
Deoxidation, activation and brightening	Oxydes

COMPATIBILITY

- Stainless steel
 - Lead-free brass
 - Silver: 800 - 925 (sterling)
 - Gold: white, pink, yellow
 - Platinum
 - Rhodium, palladium
 - Stones*:
 - Diamond, sapphire, ruby, emerald
 - Zirconium, ceramic
- *Please contact NGL before implementing a process.

COMPONENTS

- Surfactants, organic acid
- No NTA, phosphates, DEA
- No CMR compound, VOC, REACH compliant

PHYSICOCHEMICAL DATA

- pH concentrated: 0.5
- Density: 1.22
- Surface tension: 31.5 mN/m



INSTRUCTIONS FOR USE*

- Concentration: 3 to 5%
- Temperature: 30 to 60°C (86 to 140 °F)
- Time: 2 to 3 minutes

*Dependent on the quality of the water and the nature and quantity of contaminants.

PROCESS EXAMPLE

- Final cleaning and brightening



11/05/22

STORAGE CONDITIONS

- Keep the recipient hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging (HDPE).



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

