



ALLSTRIP

Universal solvent with a high flash point for the removal of blocking glues and lacquers in an ultrasonic process or in beakers.



WATCH INDUSTRY

FUNCTION	APPLICATION/POLLUTION
Ultrasonic cleaning	Removal of blocking glues and lacquers

COMPATIBILITY

- Stainless and tempered steel
- Aluminium
- Gold: white, pink, yellow
- Rhodium, palladium
- Copper alloys:
 - Brass
 - CuBe
 - Nickel silver

COMPONENTS

- No CMR compounds, REACH compliant

PHYSICOCHEMICAL DATA

- pH concentrated: n.m.
- Density: 0.99
- Flash point: 88°C (190°F)

INSTRUCTIONS FOR USE*

- Concentration: 100%
- Temperature: 20 to 50°C (68 to 122°F) (not exceed 70°C (158°F))
- Time: 2 to 10 minutes

*Use in a space that is naturally ventilated or equipped with a fume extraction system.

PROCESS EXAMPLES

- Removal of glues, waxes, lacquers, setters cement, in beakers

CLEANING	RINSING	TAP WATER RINSE	DRYING
ALLSTRIP Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min US	ALLSTRIP Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min US	Temp.: 20-30°C 68-86°F Time: 2-3 min	

- Removal of contaminants in an ultrasonic process

CLEANING	TAP WATER RINSE	DI WATER RINSE	DRYING
ALLSTRIP Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min US	GALVEX 20.02 Tap water Conc.: 2-5% Temp.: 40-70°C 104-158°F Time: 3-5 min US	Temp.: 20-30°C 68-86°F Time: 2-3 min	Temp.: 20-30°C 68-86°F Time: 1-2 min

ULTRASONIC CLEANING

Watch hands / glasses blocking glue/ lacquer

Lapping plate

Glue dissolution

Clean parts and substrates

Parameters for cleaning:

T° + % + Time + US

22/11/22

STORAGE CONDITIONS

- Keep the container hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging (HDPE).



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

