



# ALLSTRIP

Universal solvent with a high flash point for the removal of blocking glues and polishing pitch in an ultrasonic process or in beakers.



## PRECISION OPTICS RANGE

FUNCTION	APPLICATION/POLLUTION
Ultrasonic cleaning	Removal of blocking glues and polishing pitch

### COMPATIBILITY

- Photographic glasses:
  - Crown and Flint
  - Borosilicate
- UV/IR:
  - Chalcogenides
  - Fused Silica
  - Sapphire
- Calcium Fluoride and Magnesium
- Silicon (Si)
- Zinc selenide
- Zinc Sulfide
- Germanium

### COMPONENTS

- REACH compliant

### PHYSICOCHEMICAL DATA

- pH concentrated: n.m.
- Density: 0.99
- Flash point: 88°C (190°F)

### INSTRUCTIONS FOR USE\*

- Concentration: 100%
- Temperature: 20 to 50°C (68 to 122°F) (do not exceed 70°C (158°F))
- Time: 2 to 10 minutes

\*Use in a space that is naturally ventilated or equipped with a fume extraction system.

### PROCESS EXAMPLES

- Removal of blocking glues and polishing pitch in beakers

CLEANING	RINSING	RO WATER RINSE	DRYING
<b>ALLSTRIP</b> Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min US	<b>ALLSTRIP</b> Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min US	Temp.: 20-30°C 68-86°F Time: 1-2 min	

- Removal of polishing pitch, blocking glues, abrasives and final cleaning

CLEANING	OPTICAL V	RO WATER RINSE	FINISHING	RO WATER RINSE	DI WATER RINSE	DI WATER RINSE	HOT AIR DRYING
<b>ALLSTRIP</b> Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min US	<b>OPTICAL V</b> RO or DI water Conc.: 3-5% Temp.: 40-60°C 104-140°F Time: 3-5 min US	Temp.: 20-30°C 68-86°F Time: 2-3 min	<b>NANOCLEAN 2018</b> RO or DI water Conc.: 1-5% Temp.: 40-60°C 104-140°F Time: 3-5 min US	Temp.: 20-30°C 68-86°F Time: 1-2 min	Temp.: 20-30°C 68-86°F Time: 1-2 min US	Temp.: 20-30°C 68-86°F Time: 1-2 min	

### ULTRASONIC CLEANING

Magnifying glasses/glasses  
Blocking glue/polishing pitch

Lapping plate

Glue dissolution

Clean parts and substrates

Parameters for cleaning:

T° + % + Time + US

30/08/23

### STORAGE CONDITIONS

- Keep the container hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging (HDPE).



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

