



# ALLSTRIP

Solvent with a high flash point for the removal of setters cement, bloking glues, lacquers in ultrasonic cleaning or in beakers.



## AEROSPACE & AUTOMOTIVE RANGE

FUNCTION	APPLICATION/POLLUTION
Ultrasonic cleaning	Removal of setters cement, waxes, glues and lacquers

### COMPATIBILITY

- Aluminium 2024, 6061, 6082, 7075
- Titanium, TA6V
- Copper alloys:
  - Brass
  - Bronzes
- Ceramics
- Super alloys :
  - Inconel, Waspalloy, A286
- Hard steels :
  - 52100 Chrome steel, cast iron
- Bearing steels :
  - D50, 440C, 316

### COMPONENTS

- REACH compliant

### PHYSICOCHEMICAL DATA

- pH concentrated: n.m.
- Density: 0.99
- Flash point: 88°C (190°F)

### INSTRUCTIONS FOR USE\*

- Concentration: 100%
- Temperature: 20 to 50°C (68 to 122°F) (do not exceed 70°C (158°F))
- Time: 2 to 10 minutes

\*Use in a space that is naturally ventilated or equipped with a fume extraction system.

### PROCESS EXAMPLE

- Removal of waxes, glues and lacquers

#### CLEANING

ALLSTRIP	GALVEX 20.02	TAP WATER RINSE	DI WATER RINSE	DRYING
Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min	Tap water Conc.: 2-5% Temp.: 40-70°C 104-158°F Time: 3-5 min	Temp.: 20-30°C 68-86°F Time: 2-3 min	Temp.: 20-30°C 68-86°F Time: 1-2 min	

US

US



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

### ULTRASONIC CLEANING



Parameters for cleaning:



29/11/23

### STORAGE CONDITIONS

- Keep the container hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging (HDPE).

## NGL CLEANING TECHNOLOGY SA - ECOLOGICAL CLEANING SOLUTIONS

Chemin de la Vuarpillière 7 – CH-1260 NYON – SWITZERLAND  
+41 22 365 46 66 – contact@ngl-group.com – www.ngl-group.com



SWISS  
QUALITY

