



GALVEX 20.02

Universal detergent for the removal of polishing pastes, soluble oil and light pollutions in an ultrasonic process.



WATCH INDUSTRY

FUNCTION	APPLICATION/POLLUTION
Ultrasonic cleaning, interoperation, surface preparation	Soluble oils, polishing pastes, tumbling residues, etc.

COMPATIBILITY

- Stainless steel
- Gold: white, pink, yellow
- Rhodium, palladium
- Copper alloys:
 - CuBe
 - Nickel silver

COMPONENTS

- Surfactants, solubilising agent
- No NTA, phosphates, DEA
- No CMR compound, REACH compliant

PHYSICOCHEMICAL DATA

- pH concentrated: 10
- Density: 1.03
- Surface tension: 27.6 mN/m

INSTRUCTIONS FOR USE*

- Concentration: 2 to 5%
- Temperature: 40 to 70°C
- Time: 3 to 5 minutes

*Dependent on the quality of the water and the nature and quantity of contaminants.

PROCESS EXAMPLES

- Cleaning after polishing

CLEANING


GALVEX 20.02	GALVEX 20.02	TAP WATER RINSE	DI WATER RINSE	DI WATER RINSE	HOT AIR DRYING
Tap water Conc.: 2-5% Temp.: 40-70°C 104-158°F Time: 3-5 min	Tap water Conc.: 2-5% Temp.: 40-70°C 104-158°F Time: 3-5 min	Temp.: 20-30°C 68-86°F Time: 2-3 min	Temp.: 20-30°C 68-86°F Time: 1-2 min	Temp.: 20-30°C 68-86°F Time: 1-2 min	
US	US		US		

- Final cleaning and brightening

CLEANING

GALVEX 20.02	TAP WATER RINSE	RODASTEL 30	TAP WATER RINSE	DI WATER RINSE	DI WATER RINSE	HOT AIR DRYING
Tap water Conc.: 2-5% Temp.: 40-70°C 104-158°F Time: 3-5 min	Temp.: 20-30°C 68-86°F Time: 2-3 min	Tap water Conc.: 3-5% Temp.: 30-60°C 86-140°F Time: 2-3 min	Temp.: 20-30°C 68-86°F Time: 1-2 min	Temp.: 20-30°C 68-86°F Time: 1-2 min	Temp.: 20-30°C 68-86°F Time: 1-2 min	
US		US				

ULTRASONIC CLEANING



Parameters for cleaning:



Clean and bright surface.
Cleaned blind holes.

19/08/25

STORAGE CONDITIONS

- Keep the recipient hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging (HDPE).



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

NGL CLEANING TECHNOLOGY SA - ECOLOGICAL CLEANING SOLUTIONS

Chemin de la Vuarpillière 7 – CH-1260 NYON – SWITZERLAND
+41 22 365 46 66 – contact@ngl-group.com – www.ngl-group.com

SWISS
QUALITY

