



# ALLSTRIP 2025

High flash point solvent used for removing setters cement, blocking glue, varnish, in ultrasonic process.



## JEWELLERY RANGE

FUNCTION	APPLICATION/POLLUTION
Ultrasonic cleaning	Removal of setters cement, waxes, glues and lacquers

### COMPATIBILITY

- Stainless steel
  - Lead-free brass
  - Silver: 800 - 925 (sterling)
  - Gold: white, pink, yellow
  - Platinum
  - Rhodium, palladium
  - Stones\*:
    - Diamond, sapphire, ruby, emerald
    - Zirconium, ceramic
- \*Please contact NGL before implementing a process

### COMPONENTS

- Solvent
- REACH compliant

### PHYSICOCHEMICAL DATA

- pH concentrated: n.m.
- Density: 0.95
- Flash point: 88°C (190°F)

### INSTRUCTIONS FOR USE\*

- Concentration: 100%
- Temperature: 20 to 50°C (68 to 122°F) (not exceed 70°C / 158°F)
- Time: 2 to 10 minutes

\*Use in a space that is naturally ventilated or equipped with an aspiration. system.

### PROCESS EXAMPLES

- Removal of glues, waxes, lacquers and setters cements:

CLEANING	RINSING	TAP WATER RINSE	HOT AIR DRYING
<b>ALLSTRIP 2025</b> Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min US	<b>ALLSTRIP 2025</b> Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min US	Temp.: 20-30°C 68-86°F Time: 2-3 min	

- Removal of setters cement from precious metal:

CLEANING	RODACLEAN 2018	TAP WATER RINSE	FINISHING SUPER HELIT IC	TAP WATER RINSE	DI WATER RINSE	DI WATER RINSE + LIFT OUT	HOT AIR DRYING
<b>ALLSTRIP 2025</b> Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min US	RO or DI water Conc.: 3-5% Temp.: 40-70°C 104-158°F Time: 3-5 min US	Temp.: 20-30°C 68-86°F Time: 2-3 min	RO or DI water Conc.: 1-3% Temp.: 40-60°C 104-140°F Time: 3-5 min US	Temp.: 20-30°C 68-86°F Time: 2-3 min	Temp.: 20-30°C 68-86°F Time: 2-3 min	Temp.: 20-30°C 68-86°F Time: 1-2 min	

### REMOVAL OF CEMENTS OR GLUES

Setters cement

Cement dissolution with Allstrip 2025

Rinsing = cement totally removed

16/10/2025

### STORAGE CONDITIONS

- Keep the recipient hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging (HDPE).



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

