



ALLSTRIP 2025

High flash point solvent used for removing setters cement, blocking glue, varnish, in ultrasonic process.



WATCH INDUSTRY

FUNCTION	APPLICATION/POLLUTION
Ultrasonic cleaning	Removal of setters cement, waxes, glues and lacquers

COMPATIBILITY

- Copper alloys:
 - Brass, with and without lead
 - Cuproal, cupronickel, bronze, nickel silver
- Precious metals :
 - Gold, Silver, Platinum/Titanium
- Hardened steels:
 - Durnico, Maraging, 20AP
- Stainless steels:
 - Austenitic (303, 304, 316)
 - Martensitic (420, PH)
- Ceramics

COMPONENTS

- Solvent
- REACH compliant

PHYSICO-CHEMICAL DATA

- pH concentrated: n.m.
- Density: 0.95
- Flash point: 88°C (190°F)

INSTRUCTIONS FOR USE*

- Concentration: 100%
- Temperature: 20 to 50°C (68 to 122°F) (not exceed 70°C (158°F))
- Time: 2 to 10 minutes

*Use in a space that is naturally ventilated or equipped with a fume extraction system.

PROCESS EXAMPLES

- Removal of glues, waxes, lacquers and setters cement:

CLEANING	RINSING	TAP WATER RINSE	HOT AIR DRYING
ALLSTRIP 2025 Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min US	ALLSTRIP 2025 Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min US	Temp.: 20-30°C 68-86°F Time: 2-3 min	

- Removal of setters cement from precious metal

CLEANING	RODACLEAN 2018	TAP WATER RINSE	FINISHING	TAP WATER RINSE	DI WATER RINSE	DI WATER RINSE + LIFT OUT	HOT AIR DRYING
ALLSTRIP 2025 Conc.: 100% Temp.: 20-50°C 68-122°F Time: 2-10 min US	RODACLEAN 2018 RO or DI water Conc.: 3-5% Temp.: 40-70°C 104-158°F Time: 3-5 min US	Temp.: 20-30°C 68-86°F Time: 2-3 min	SUPER HELIT IC RO or DI water Conc.: 1-3% Temp.: 40-60°C 104-140°F Time: 3-5 min US	Temp.: 20-30°C 68-86°F Time: 2-3 min	Temp.: 20-30°C 68-86°F Time: 2-3 min	Temp.: 20-30°C 68-86°F Time: 1-2 min	

ULTRASONIC CLEANING

Watch hands / glasses blocking glue/ lacquer

Glue dissolution

Clean parts and substrates

Parameters for cleaning:

T° + % + Time + US

16/10/2025

STORAGE CONDITIONS

- Keep the container hermetically sealed between 5°C and 40°C (41°F and 104°F) in a dry place.
- Always keep in packaging made from the same material as the original packaging (HDPE).



If you have any questions, please contact our Application Centre on: +41 22 365 46 66

